



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08L 7/02, C08J 5/18, C05F 17/02	A1	(11) International Publication Number: WO 99/48969 (43) International Publication Date: 30 September 1999 (30.09.99)
(21) International Application Number: PCT/EP99/02053 (22) International Filing Date: 18 March 1999 (18.03.99) (30) Priority Data: 10-078743 26 March 1998 (26.03.98) JP (71) Applicant (for all designated States except US): ELF ATOCHEM S.A. [FR/FR]; 4/8, cours Michelet, F-92080 Puteaux (FR). (72) Inventors; and (75) Inventors/Applicants (for US only): ISHINO, Kiyotaka [JP/JP]; Elf Atochem Japan Kyoto Technical Center, Science Center Building 3, Kyoto Research Park, 1 Chudoji Awato-cho, Shimogyo-ku, Kyoto-shi, Kyoto-fu, Kyoto 600 (JP). KURATSUJI, Takatoshi [JP/JP]; Elf Atochem Japan Kyoto Technical Center, Science Center Building 3, Kyoto Research Park, 1 Chudoji Awato-cho, Shimogyo-ku, Kyoto-shi, Kyoto-fu, Kyoto 600 (JP). YAMAMOTO, Jun [JP/JP]; Elf Atochem Japan Kyoto Technical Center, Science Center Building 3, Kyoto Research Park, 1 Chudoji Awato-cho, Shimogyo-ku, Kyoto-shi, Kyoto-fu, Kyoto 600 (JP). IKETAKI, Takashi [JP/JP]; Nishi 2-7, Inada-cho, Obihiro-shi, Hokkaido (JP).		(74) Agent: NEEL, Henry; ELF Atochem S.A., Dept. Propriété Industrielle, Cours Michelet - La Défense 10, F-92091 Paris La Défense Cedex (FR). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FILM FOR ACCELERATED COMPOST FERMENTATION (57) Abstract <p>Objective: the objective of the present invention lies in shortening the compost preparation period by a simple method and preventing contamination of underground water. Constitution: film for accelerated compost fermentation which is characterized in that it comprises a composition in which the chief component is polymer containing polyether chains as structural units, and where the water vapour permeability thereof is at least 300 g/m².24h, the oxygen permeability is at least 1,000 cm³/m².24h.atm and the carbon dioxide permeability is at least 10,000 cm³/m².24h.atm; together with film for accelerated compost fermentation which is characterized in that the aforesaid film is reinforced by means of a nonwoven material or net.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

[Title of the Invention]

FILM FOR ACCELERATED COMPOST FERMENTATION

[Detailed Description of the Invention]

[0001]

[Industrial Field of Application]

The present invention relates to film for accelerated compost fermentation. The objective thereof lies in shortening the fermentation period and preventing underground water pollution.

[0002]

[Prior-Art]

Compost is obtained by aerobic microbial fermentation after mixing straw, rice chaff, weeds or the like with the excreta of domestic animals. Consequently, for obtaining a good quality compost it is necessary to have sufficient oxygen and a suitable level of temperature and moisture and, hitherto, the following methods have been adopted primarily.

First of all, in regard to the traditional method based on forming a heap, there has been the problem that, when the weather is fine, the surface dries out and hardens, so that air (oxygen) cannot readily pass into the interior and the fermentation is slowed, while, when it is raining, the moisture soaks into the interior, so that the composting materials are cooled and the fermentation is incomplete. Moreover, contaminated water soaks underground, which brings about the problem of under-ground water pollution.

[0003]

To overcome such difficulties, covering with polyvinyl chloride or polyethylene sheet has been tried to some extent but, with such sheet, not only is there a build-up of water vapour and carbon dioxide in the interior when the weather is fine but also the supply of oxygen is inadequate, so that aerobic fermentation by the micro-organisms is impeded and therefore the sheet has to be removed. However, at night, to cope with when it rains, it is necessary to cover over with the sheet again, so there is the problem of the nuisance of having to place and then remove the sheet.

[0004]

On the other hand, methods have been proposed using special apparatus and equipment, so that air is circulated and the temperature controlled, and these methods are to some extent being employed in practice (see, for example, Japanese Unexamined Patent Publication Nos 55-51788, 57-123883,

60-260490, 3-237081, 3-261690, 4-59685, 5-170585, 7-277866, 7-98711 and 2524040).

At the same time, methods for accelerating fermentation using microbial decomposition accelerators have also been tried, as described in Japanese Unexamined Patent Publication No. 9-110571.

However, not only do these methods generally require equipment investment by the farmer, but also the procedure is complex and the equipment maintenance requires time, so a more simple, improved, method has been demanded.

[0005]

[Problem to be Resolved by the Invention]

The present inventors have carried out a painstaking investigation aimed at providing protection from rain-water by a simple method and shortening the fermentation time, as a result of which they have discovered that by using a film which is water impermeable but through which water vapour and gases can pass, this objective is realised. The present invention is based on this discovery.

[0006]

[Means for Resolving the Problem]

The present invention is a film for accelerated compost fermentation which is characterized in that it comprises a composition in which the chief component is polymer containing polyether chains as structural units, and the water vapour permeability thereof is at least 300 g/m².24h, the oxygen permeability is at least 1,000 cm³/m².24h.atm and the carbon dioxide permeability is at least 10,000 cm³/m².24h.atm; together with film for accelerated compost fermentation which is characterized in that the aforesaid film is reinforced by means of a nonwoven material or net.

[0007]

In the present invention, "polymer containing polyether chains as structural units" refers to a block copolymer in which polyoxyalkylene chains and other polymer chains are linked together, or polymer in which polyoxyalkylene chains are linked together via connecting regions. As examples of the polyoxyalkylene here, there are poly-oxyethylene, poly(1,2- and 1,3-oxypropylene), polyoxy-tetramethylene, polyoxyhexamethylene, block or random copolymers of ethylene oxide and propylene oxide, and block or random copolymers of ethylene oxide and tetra-hydrofuran. In particular, it is preferred that the number of carbons in the alkylene moiety be from 2 to 4, with polyoxyethylene being most preferred. The number average molecular weight of the polyoxyalkylene is from 200 to 6000, and preferably from 300 to 4000.

[0008]

In the present invention, as examples of desirably used "polymer containing polyether chains as structural units" there are polyetherpolyamide block copolymers, polyether-polyester block copolymers and polyetherurethanes. Of these, the polyetherpolyamide block copolymers are particularly preferred.

[0009]

The "polyetherpolyamide block copolymers" used in the present invention are polymers in which there are linked together polyoxyalkylene chains (a) and polyamide chains (b) which are the polymers of aminocarboxylic acids or lactams with 6 or more carbon atoms, or of the salts of dicarboxylic acids and diamines with 6 or more carbon atoms. Where (a) and (b) are mutually connected via a dicarboxylic acid (c) having from 4 to 20 carbons, the polymer is generally referred to as a polyetherester-amide, and such polymer is also included. Here, as the "aminocarboxylic acids or lactams with 6 or more carbon atoms, or salts of dicarboxylic acids and diamines with 6 or more carbon atoms", 11-aminoundecanoic acid, 12-aminododecanoic acid, caprolactam, laurolactam, the salt of hexamethylenediamine + adipic acid and the salt of hexamethylenediamine + sebacic acid are preferably used. Again, there may be jointly used two or more types of aforesaid components (a) and (b).

[0010]

Such polymer may be produced, for example, by the method described in Japanese Examined Patent Publication No. 56-45419. The type and weight ratio of the polyether component and the polyamide component in the block copolymer used in the present invention are selected according to the objectives and the application. From the point of view of water vapour permeability, gas permeability, water resistance and handling properties, etc, the ratio of the polyether/polyamide is preferably from 4/1 to 1/4.

[0011]

The "polyetherpolyester block copolymer" used in the present invention is one in which there are linked together polyoxyalkylene chains (a) and polyester chains (d) comprising polymer of a hydroxycarboxylic acid with at least six carbons or of a dihydroxy compound with at least two carbons and an aromatic dicarboxylic acid. Again, in regard to these (a) and (d) components, two or more types may be jointly employed. Such polymer is produced for example by the method described in US Patent 4,739,012. The weight ratio of the aforesaid (a) and (d) components in the block copolymer employed in the present invention is determined by the objectives and the application.

[0012]

The 'polyetherurethane' employed in the present invention is a thermoplastic polyurethane employing polyether as the soft segments, but there is little effect with a polyester type or caprolactone type even though they are also polyurethanes. Specifically, the polyurethanes are normally obtained by the reaction of an organic diisocyanate and a polyether of molecular weight from

500 to 6000 with, in some cases, the chain extension being carried out in the presence of catalyst. As the isocyanate, there is preferably employed tolylene diisocyanate, diphenylmethane diisocyanate or the like, and as the polyether there is preferably used polytetramethylene glycol or polypropylene oxide, etc.

[0013]

In the present invention, "composition in which the chief component is polymer containing polyether chains as structural units" means a polyetherpolyamide block copolymer, polyetherpolyester block copolymer or polyetherurethane on its own, a mixture of these, or, in the case of the block copolymers, mixtures of two types of polymer in which the resin soft segment/hard segment type or content differs. It also includes blends with some other resin. As examples of the resins which can be blended to produce the composition, there are polyolefins such as polyethylene and the copolymers of polyethylene and acrylate. In the case where blending is carried out with another resin, there may also be incorporated a compatibilizing agent such as an ethylene copolymer or graft copolymer with unsaturated epoxy groups or acid anhydride groups, or an acrylate copolymer.

The type and ratio of the resin other than the polymer with polyether structural units will be selected such that the water vapour and gas permeabilities lie within the following ranges.

[0014]

The film of the present invention needs to have a water vapour permeability of at least 300 g/m².24h, an oxygen permeability of at least 1,000 cm³/m².24h.atm and a carbon dioxide permeability of at least 10,000 cm³/m².24h.atm. Preferably, the water vapour permeability is at least 1000 g/m².24h, the oxygen permeability is at least 3,000 cm³/m².24h.atm and the carbon dioxide permeability is at least 30,000 cm³/m².24h.atm, and more preferably the water vapour permeability is at least 2000 g/m².24h, the oxygen permeability is at least 5,000 cm³/m².24h.atm and the carbon dioxide permeability is at least 50,000 cm³/m².24h.atm.

[0015]

If the water vapour permeability is less than 300 g/m².24h, then the interior moisture will increase. If the carbon dioxide permeability is less than 10,000 cm³/m².24h.atm, there is a build-up of carbon dioxide gas in the interior and if the oxygen permeability is less than 1,000 cm³/m².24h.atm, then there is an insufficient supply of oxygen to the interior, so that anaerobic fermentation occurs and a good quality compost is not obtained.

[0016]

In the composition in which the chief component is polymer containing polyether chains as structural units, there may be freely included known antioxidants, thermal decomposition preventives, ultraviolet absorbers, hydrolysis resistance improvers, colouring agents (dyes and pigments), antistatic agents, electro-

conductors, crystallization nucleating agents, crystallization promoters, plasticizers, ready slip agents, lubricating agents, release agents, flame retardants and flame retarding auxiliaries, within a range such that the characteristics of the present invention are not impaired. In regard to the method for producing film from this composition, there can be used the T-die extrusion method or the inflation method, with film formation being conducted by passage through a T-die or an inflation die, etc. The extrusion temperature will depend on the resin type and the blending ratio but, in general, it is from 120 to 250°C.

[0017]

The film of the present invention is mostly used outdoors, so in cases where strength is required it is still more effective to carry out reinforcement with a nonwoven material or net. As the nonwoven material, there can be used one which comprises polyamide or polyester fibre. A polyolefin net or the like can also be used.

In the case of a nonwoven material or net, a two layer structure (with the nonwoven material or net on the outside) or a three layer structure (with the film interposed between nonwoven material or net) may be used. However, it is necessary to select a material, form and thickness such that the water vapour and gas permeability are not impaired.

[0018]

[Examples]

Below, the present invention is explained by means of examples but it goes without saying that the present invention is not to be restricted just to these. Now, in the examples, the various properties were measured by the following methods.

(1) Water vapour permeability (units: g/m².24h)

The film was subjected to measurement under conditions B (40°C, 90% relative humidity) based on JIS Z0208.

(2) Gas permeability (units: cc/m².24h.atm or %)

Measurement was carried out by the pressure difference method. The specific conditions were as follows.

Equipment: gas permeability measurement device model GTR-10XE produced by the Yanako Bunseki Kogyo (Co.).

Measurement area: 15.2 cm² (44 mm diameter)

Detection method: calibration curve method based on a gas chromatograph fitted with a TCD

Temperature, relative humidity: 25°C, 0% RH

Carrier gas: helium, 70 KPa

Diffusion gas: CO₂/O₂/N₂/C₂H₄ (30.0/30.0/39.12/0.88 vol%)

[0019]

Further, the films employed in the present invention were as follows.

A-1: Film of thickness 25 microns comprising polyetherester-polyamide block copolymer consisting of polyoxyethylene chains and polyamide 12 chains (weight ratio 1/3)

The permeabilities of this film were as follows.

water vapour permeability: 5,100 g/m².24h
oxygen permeability: 3,700 cm³/m².24h.atm
carbon dioxide permeability: 55,000 cm³/m².24h.atm

A-2: Film of thickness 25 microns comprising a composition consisting of polyetherester-polyamide block copolymer composed of polyoxyethylene chains and polyamide 12 chains (weight ratio 1/1), and ethylene-butyl acrylate copolymer, (weight ratio of composition = 65/35)

The permeabilities of this film were as follows.

water vapour permeability: 4,000 g/m².24h
oxygen permeability: 109,000 cm³/m².24h.atm
carbon dioxide permeability: 27,000 cm³/m².24h.atm

A-2: Film A-2 laminated and reinforced with a polyamide 6 nonwoven

B-2: Commercial plasticized vinyl chloride film for agriculture

water vapour permeability: 40 g/m².24h
oxygen permeability: 1,800 cm³/m².24h.atm
carbon dioxide permeability: 12,000 cm³/m².24h.atm

[0020]

[Example 1, Comparative Example 1]

Composts were prepared in five sections, in each of which had been compressed compost material comprising straw mixed with cow dung to a size of height about 2 m, width about 3 m and length about 20 m, and covered respectively with A-1, A-2, A-3, B-1 and B-0 [compost heap with no film]. Now, excepting that turning of the heap was carried out every month, they were left covered with the film. On each such occasion, the compost weight and the compost

composition (moisture, organic material and chief inorganic materials content) were measured. Further, the temperature of the compost was monitored with a temperature sensor.

In the case of the A-1, A-2 and A-3 composts, at the time of the third monthly turning of the heap, the straw had decomposed for the most part and it was concluded that the fermentation had proceeded fully. Now, when exposed to a strong wind, A-2 was seen to have suffered some damage, but no damage was noted for A-3 which was reinforced with a nonwoven material.

Table 1 shows the change in compost weight, moisture content and temperature for A-1, B-0 and B-1.

[Table 1]

Change in Compost Weight, Moisture and Temperature

	A-1	B-0	B-1
Total Weight (1)			
after 0 month	100	100	100
after 1 month	81	87	89
after 2 months	74	85	84
after 3 months	62	84	76
Moisture %			
after 0 month	66	62	70
after 1 month	60	67	66
after 2 months	65	63	65
after 3 months	64	65	67
Temperature °C			
0-1 months	40-60	45-65	30-55
1-2 month	35-58	25-55	30-45
2-3 months	20-40	3-35	20-30

1) The weight at 0 month being taken as 100%

From Table 1, the weight reduction was most rapid in section A-1 compared to the others. This was because the water vapour permeability was high but there was no penetration of rain water. Furthermore, the moisture content was largely kept constant at a suitable level, and the temperature too moved within a reasonable range of 40-60°. For these reasons, it is concluded that microbial fermentation occurred rapidly. Moreover, in terms of the weight reduction, since after 3 months this had already reached the same level as ordinary completely composted material, it was concluded that the fermentation was complete. On the other hand in the case of section B-1, since the moisture vapour permeability was low, moisture evaporation was suppressed and the reduction in weight was

slow. Moreover, since the temperature was low, it is thought that there was little heat evolution due to aerobic fermentation by the micro-organisms. Table 2 shows the compositions of the composts after 3 months for A-1, B-0 and B-1.

[Table 2]

Compost Composition

	A-1	B-0	B-1	Good Compost
total carbon (%)	24.5	23.3	26.5	30-40
total nitrogen (%)	2.2	1.8	1.9	≥ 2.2
CaO (%)	2.9	2.5	2.7	≥ 2.4
K ₂ O (%)	4.2	4.1	4.5	≥ 4.0
electrical conductivity ms/cm.s	8.2	6.7	7.1	≥ 7.8

From Table 2, it can be seen that although the total carbon in section A-1 was slightly low, the total nitrogen exceeded 2% and the CaO and K₂O were at least the specified values, while electrical conductivity which indicates activity was 8 ms/cm.s, and so a good compost was obtained. On the other hand, in the case of B-0 and B-1, the total nitrogen and the electrical conductivity were low and a good compost was not obtained after 3 months.

[0021]

[Effects of the Invention]

As explained above, by employing film through which water does not pass but through which water vapour and gas can permeate, the present invention offers simple protection against rainwater and shortens the fermentation period.

[Scope of Claims]

[Claim 1] Film for accelerated compost fermentation which is characterized in that it comprises a composition in which the chief component is polymer containing polyether chains as structural units, and the water vapour permeability thereof is at least 300 g/m².24h, the oxygen permeability is at least 1,000 cm³/m².24h.atm and the carbon dioxide permeability is at least 10,000 cm³/m².24h.atm.

[Claim 2] Film according to Claim 1 which is characterized in that the polymer containing polyether chains as structural units is of at least one type selected from the group comprising polyetherpolyamide block copolymers, polyetherpolyester block copolymers and polyetherurethanes.

[Claim 3] Film according to Claim 1 where the film of Claim 1 is reinforced by means of a nonwoven material or net.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02053

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L71/02 C08J5/18 C05F17/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L C08J C08G C05F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 660 887 A (NUSSBAUMER WALTER ET AL) 26 August 1997 (1997-08-26) claim 1 column 3, line 32	1-3
X	--- KAPLAN W A ET AL: "THE EFFECT OF POLYMER STRUCTURE ON THE GAS PERMEABILITY OF MODEL POLYURETHANES" JOURNAL OF CELLULAR PLASTICS, vol. 30, no. 3, 1 May 1994 (1994-05-01), pages 242-272, XP000443643 ISSN: 0021-955X tables 2A,B	1,2
X	--- EP 0 378 015 A (ATOCHEM ELF SA) 18 July 1990 (1990-07-18) claim 1 ---	1,2
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

22 July 1999

Date of mailing of the international search report

12. 08. 1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

O'Sullivan, T

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02053

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 44 40 837 A (BASF AG) 23 May 1996 (1996-05-23) claim 1 page 8, line 65 - line 66 ---	1,2
A	US 3 895 916 A (ROSNER KURT) 22 July 1975 (1975-07-22) figures 1-4 -----	1-3

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/02053

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5660887 A	26-08-1997	DE 4121716 A	14-01-1993
		US 5883217 A	16-03-1999
		AT 179450 T	15-05-1999
		CA 2072839 A	02-01-1993
		DE 4143454 C	05-01-1995
		DE 59209682 D	02-06-1999
		EP 0522321 A	13-01-1993
		JP 5209162 A	20-08-1993
		MX 9203828 A	01-03-1993
		US 5869593 A	09-02-1999
		US 5851661 A	22-12-1998
		US 5508371 A	16-04-1996
EP 0378015 A	18-07-1990	FR 2639644 A	01-06-1990
		AT 117333 T	15-02-1995
		AU 627523 B	27-08-1992
		AU 4547889 A	31-05-1990
		CA 2003489 A,C	25-05-1990
		CN 1042926 A,B	13-06-1990
		CN 1096308 A,B	14-12-1994
		DE 68920724 D	02-03-1995
		DE 68920724 T	24-08-1995
		DK 591289 A	26-05-1990
		ES 2066872 T	16-03-1995
		FI 99130 B	30-06-1997
		GR 3015515 T	30-06-1995
		HK 177795 A	01-12-1995
		IE 70669 B	11-12-1996
		IL 92304 A	25-01-1994
		JP 2199131 A	07-08-1990
		JP 2572135 B	16-01-1997
		KR 9311366 B	04-12-1993
		NO 305321 B	10-05-1999
		PT 92402 A,B	31-05-1990
		US 5506024 A	09-04-1996
DE 4440837 A	23-05-1996	AU 691317 B	14-05-1998
		AU 2978195 A	06-06-1996
		CA 2205072 A	23-05-1996
		CN 1170419 A	14-01-1998
		CZ 9701465 A	15-10-1997
		WO 9615174 A	23-05-1996
		EP 0792310 A	03-09-1997
		FI 972060 A	14-05-1997
		HU 77057 A	02-03-1998
		JP 11500468 T	12-01-1999
		NO 972227 A	14-07-1997
		NZ 289823 A	26-06-1998
		PL 320223 A	15-09-1997
US 3895916 A	22-07-1975	AT 319287 B	10-12-1974
		AU 5599173 A	28-11-1974
		BE 799009 A	31-08-1973
		CA 976779 A	28-10-1975
		CH 587202 A	29-04-1977
		DE 2226729 A	13-12-1973
		FR 2186405 A	11-01-1974
		GB 1381848 A	29-01-1975

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/02053

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3895916 A		JP 1005335 C	24-07-1980
		JP 49084857 A	14-08-1974
		JP 54037230 B	14-11-1979
		NL 7306629 A,C	04-12-1973
